

CRACK FILLER

High Strength Non-Shrink Crack Powder on Surface



PRODUCT DESCRIPTION

Crack Filler is a Non-shrink, High Strength specially formulated, Polymer Modified Powder for Filling Cracks in plastered surfaces. Crack Filler powder when mixed with water forms a creamy consistent paste, which is easy to use for filling cracks in plastered surfaces. By adding specific quantity of water, it can be used as putty for a plastered surface.

ADVANTAGES

- Accommodates movements in the cracks.
- Over-Quotable after curing.
- Single Component and needs only mixing with water.
- Replaces Costly Sealants and Putties.
- No Shrinkage.
- Excellent Adhesion.
- It can be used as putty on plastered surfaces in Patch works.

USES

- Repairing of internal and external cracks in plastered surfaces up to 5 mm X 5 mm size.

TECHNICAL INFORMATION

- **Coverage:** Approx. 20 running meters/ kg for 5 mm x 5 mm Crack.
- **Nature:** White Coloured Powder, also available in Colours on demand.
- **Storage:** Store in a Cool and Dry Place.
- **Shelf Life:** 1 year.

METHOD OF APPLICATION

- Clean the crack to remove all the loose material. If the crack is too fine, it must be broken to ascertain its actual width and depth. Ensure the surface is free from oil, dust and grease.
- Mix Crack Filler powder in clean water in the proportion 100 gm. of Crack Filler powder &

30 – 35 gm. of water by volume.

- Moisten the surface slightly before applying Crack Filler powder.
- Press Crack Filler powder Paste into the cracks using a spatula or putty knife.
- Level the surface with a Putty knife to get a smooth & clean surface.
- Painting operation can start after 24 hours when Crack Filler powder is completely cured.
- For putty add water till a smooth consistent paste is achieved.
- Add acrylic emulsion paint 5% to get more flexibility & workability.

PACKING

Crack Filler Available in 1 kg Packing.

HEALTH & SAFETY

Please refer to Safety Data Sheet.

CAUTIONS

- Crack Filler Powder is Strictly not recommended to fill Cracks more than 5 mm.
- Strictly not for filling structural Cracks/Expansion joints/Construction joints/Separation gaps.
- Painting Should Commence after 24 hours.

Highbond Coatings Pvt Ltd

Sr. No. 70/2B/1, Flat No 101 & 102,
Purushottam Villa, Vadgaon Bk,
Pune – 411041

Tel: +91 9370953995

Mail: info@highbondcoatings.com